



# Superior Finishes



*Superior Finish is Master Wall's textured finish line. Refinish is used for creating a textured surface using a variety of techniques or as a leveling coat when refinishing old textures. Available in standard or custom colors, Refinish may be applied over Master Wall Base Coats or prepared substrates including brick, masonry, concrete and stucco. Superior Finishes work great for interior applications as well. Refinish is available in five-gallon (19L) pails and is typically troweled onto the wall surface with a stainless steel trowel.*

## Refinish Texture

### Integrally Colored Finish



#### Finish Properties

Meets or Exceeds:  
 ASTM E84 Surface Burning  
 ASTM C67 Freeze/Thaw  
 ASTM D2247 Humidity  
 ASTM D3273 Mold/Mildew  
 ASTM D968 Abrasion  
 ASTM B117 Salt Spray  
 ASTM G53 Weathering  
 ASTM G23 Weathering

#### Application Procedure

**Job Conditions** - Air and substrate temperature for application of *Superior Finishes* must be 40°F (5°C) or higher and must remain 40°F (5°C) or higher for a minimum of 24 hours. Provide temporary protection to protect the wall system from damage until permanent flashings, caps and sealants are installed. Store materials within prescribed temperature limits and out of direct sunlight. High temperatures will reduce working times, Low temperatures and/or high humidity will extend working, set and dry times.

**Preparation** - The substrate must be approved by Master Wall Inc., clean, dry, structurally sound and free of efflorescence, oil, grease, form release agents and curing compounds or anything that would affect bond. Painted surfaces are not acceptable and must be removed. Concrete and surfaces should cure for a minimum of 28 days. Stucco should be cured until clean, dry and hard—typically 14 days.

Interior drywall should be finished and made ready for paint. Prime surfaces with *Primecoat* primer prior to finishing.

**Base Coats** - Must be flat, dry hard, and free of efflorescence. Master Wall base coats must cure a minimum of 12 hours before application of Superior Finish. Substrates of brick, masonry or concrete should be leveled smooth using either Master Wall base coats or stucco.

**Mixing** - Thoroughly stir *Superior Finish* using a heavy duty 1/2" (12.7 mm) drill at 400 - 500 rpm and a heavy duty mixing paddle. Small amounts of clean, potable water may be added to obtain a workable consistency. To avoid color variations, add the same amount of water to each pail. Do not exceed 24 ounces (0.7L) of water per pail of finish.

#### Approved Substrates

Master Wall Base Coats  
 Stucco  
 Prepared & Base Coated  
 Surfaces of:  
 Brick  
 Concrete  
 Masonry  
 Others approved in writing

**Application** — Apply *Refinish* to match the approved sample texture or effect using the selected tools and techniques. Use stainless steel tools.

#### **For Professional Results**

- Apply finish coats away from direct sunlight. Cold joints or color variations can occur if the finish dries too quickly.
- Consider priming stucco surfaces with *Primecoat* to even out finish absorption.
- Surfaces exposed to the weather must be sloped (6:12 minimum).

#### Statistics

##### Coverage (Estimated/Varies)

Varies with technique

Pail Weight: 70 lbs (32kg)

Working Time: 1/4 hour @ room temperature

Drying Time: 8-12 hours to set, 48-72 hours to dry @ room temperature

Application Range: 40°-110°F (5°-43°C)

Shelf Life: 2 years

- Finishes are intended for the approved substrates listed above and should not be applied directly to gypsum board or insulation board products.

**Clean Up**—Tools and equipment can be cleaned with soapy water while the *Superior Finish* is still wet.



Information contained in this product data sheet conforms to the standard detail recommendations and specifications for the installation of Master Wall Inc. products and is presented in good faith. Master Wall Inc. assumes no liability, expressed or implied as to the architecture, engineering, or workmanship of any project. This information may be concurrent with, or superseded by other applicable documents, such as specifications and details. Contact Master Wall Inc. for the most current product information.

P. O. Box 397  
 Fortson, GA 31808  
 800-755-0825  
 Technical 800-760-2861  
[www.masterwall.com](http://www.masterwall.com)